

**ROLLFLOOR BR 2,7 mm**

| Characteristics EN 12199            | Standard                            | Unit            | Requirements                           | Average values from production |
|-------------------------------------|-------------------------------------|-----------------|--|--------------------------------|
| Hardness                            | ISO 7619                            | shore A         | ≥ 70                                   | comply                         |
| Residual indentation                | EN/ISO 24343-1 (EN 433)             | mm              | ≤ 0,20                                 | comply                         |
| Abrasion resistance                 | ISO 4649 (Met. A - 5N)              | mm <sup>3</sup> | ≤ 250                                  | comply                         |
| Dimensional stability               | EN/ISO 23999 (EN 434)               | %               | ± 0,40 max                             | comply                         |
| Flexibility                         | EN/ISO 24344 Met. A Ø 20mm (EN 435) | -               | pas de fissuration                     | comply                         |
| Colour fastness to artificial light | ISO 105-B02 Met. 3                  | degré           | ≥ 6 bleue échelle<br>≥ 3 grise échelle | comply                         |
| Cigarette burn                      | EN 1399                             | rating          | met. A ≥ 4<br>met. B ≥ 3               | comply                         |
| <b>Characteristics EN 14041</b>     |                                     |                 |  |                                |
| Fire behaviour                      | EN 13501-1                          | class           | -                                      | Cfl – sI bonded                |
| Slip resistance                     | EN 13893                            | class           | ≥ 0,30 (DS)                            | DS                             |
| <b>Other characteristics</b>        |                                     |                 |  |                                |
| Resistance to stains                | EN/ISO 26987 (EN 423)               | -               | -                                      | resistant *                    |
| Electrical resistance               | EN 1081 Met. A                      | ohm             | -                                      | > 10 <sup>10</sup>             |
| Electrostatic charge                | EN 1815                             | kV              | -                                      | ≤ 2 (antistatique)             |

\* depending on concentration and time of contact, for specific agent please ask.




2,7 mm

3,8 kg/m<sup>2</sup>

1,0 m



10 m

**Classification EN ISO 10874 (EN 685):**

The data declared by the manufacturer shall be taken as average: single values change amongst batches and colours.