





ECOSAFE

Technical datasheet

Technical parameter	Standard	Unit	Result
DESCRIPTION			
Construction			compact heterogeneous
Total thickness	EN ISO 24346	mm	2,0
Wear layer thickness	EN ISO 24340	mm	0,7
Width of roll	EN ISO 24341	m	2
Length of roll	EN ISO 24341	lm	20
Total weight	EN ISO 23997	kg/m ²	2,8
CLASSIFICATION			
European classification	EN 685	class	34/43
PERFORMANCE			
Abrasion group	MSZ EN 660-1	class	T
Residual indentation	EN ISO 24343	max. mm	0,1
Dimensional stability	EN ISO 23999	max.%	0,2
Fire resistance	EN 13501-1	class	Bfl-s1
	DIN 4102/ÖNORM	class	B1
	ASTM E 648/ 662	class	Class 1
	Gost 30402-94		G1
Slip resistance	DIN 51130		R10
	ASTM D2047-99		dry: 0,92 / wet: 0,84
	EN 13893	class	DS
	RRL Pendulum Test		>36 (wet test)
Abrasion resistance	ISO 9352	g/1000 circle	-0,25
Abrasion resistance	ASTM D3884-01	g/1000 circle	-0,19
Chemical resistance	EN ISO 26987		✓
	ASTM F925-02		✓
Light fastness	EN 20105 B02	grade	6
Castor chair resistance	EN ISO 4918		✓
Surface treatment			Easy Care PUR
Anti-bacterial and fungicid treatment			graboSAN
Enviromental attributes	 		Phthalate, Solvent and Heavy metal free product
Seaming method			heat or cold weld
Warranty		year	10
CE MARKING	EN 14041		✓