



\* FOR ILLUSTRATION PURPOSE ONLY-PICTURES MAY VARY FROM ACTUAL SAMPLE

**PROMASTER TEST REPORT**

TEST ITEM	UNIT	PLANK				
		SPECIFICATION	RESULTS	SPECIFICATION	RESULTS	
APPEARANCE	-	NO DEFECT	NO DEFECT	NO DEFECT	NO DEFECT	
THICKNESS	mm	3.0 ± 0.15	3.04	3.0 ± 0.15	2.98	
LENGTH	mm	940 ± 0.45	940.2	914.4 ± 0.9	914.9	
WIDTH	mm	186 ± 0.45	185.9	100 ± 1.10	100.03	
PERPENDICULARITY	mm	0.25 ↓	0.11	0.25 ↓	0.11	
RESIDUAL INDENTATION	%	8.0 ↓	3.2	8.0 ↓	3.1	
HEATING LOSS	wt%	0.5 ↓	0.1	0.5 ↓	0.1	
DIMENSIONAL STABILITY by HEATING	T.D	%	0.25 ↓	0.02	0.25 ↓	0.07
	M.D	%	0.25 ↓	0.03	0.25 ↓	0.08
INDENTATION	20°C	mm	0.25 ↓	0.43	0.25 ↓	0.39
	45°C	mm	1.20 ↓	0.6	1.20 ↓	0.6
CHEMICAL RESISTANCE	SOYBEAN OIL	-	NO DEFECT	NO DEFECT	NO DEFECT	NO DEFECT
	LUBRICANT	-				
	95% ETHYLALCOHOL	-				
	10% AMMONIUM HYDROXIDE	-				
	MILK	-				
	5% ACETIC ACID	-				
	5% HYDROCHLORIC ACID	-				
	KEROSENE	-				
	SOY SAUCE	-				
CEMENT PASTE	-					
SCRATCHING TEST	95% ETHANOL	mm	3.1 ↓	1.8	3.1 ↓	1.7
	2% SODIUM HYDROXIDE	mm	3.1 ↓	1.7	3.1 ↓	1.8
	SOYBEAN OIL	mm	3.1 ↓	1.6	3.1 ↓	1.7
	KEROSENE	mm	3.1 ↓	2.5	3.1 ↓	2.5



**PREMIER WOOD** • Dimension : 180mm x 920mm • Total Thickness : 3.0mm • Package : 20Pcs/Box(3.31m<sup>2</sup>)



Block Oak PW-801



Dark Block Oak PW-802



Line Wood PW-807



Dark Line Wood PW-808

NOX PRIME TILE®

**WIDE WOOD** • Dimension : 186mm x 940mm • Total Thickness : 3.0mm • Package : 19Pcs/Box(3.32m<sup>2</sup>)



*image of this catalogue can be different from real products due to the print condition. There can be gnarl patterns at woods products for realistic textures.*

**WOOD PLANK** • Dimension : 101.6mm x 914.4mm • Total Thickness : 3.0mm • Package : 36Pcs/Box(3.29m<sup>2</sup>)



Light Pine WP 805



Walnut WP 830



Antique Oak WP 840



Chestnut WP 804



Antique Pine WW-817



Antique Timber WW-839



Pine WW-837



Oak WW-825



Dark Timber WW-823



Timber WW-821



Dark Walnut WW-833



Ash WW-3334

